

ONKAPOX WET 365

SOLVENT FREE EPOXY MOISTURE BARRIER

PRODUCT DEFINITION

ONKAPOX WET 365 is a two-component, solvent-free, epoxy based moisture barrier.

AREA OF USE

ONKAPOX WET 365, the two-component, water-based Epoxy treatment and impregnation primer. Does not contain any fillers or pigments. Penetrates to capillary pores due to its low viscosity. Perfectly diffuses to fresh concrete. Effective against negative pressure. Dries fast. Does not contain any volatile organic compounds. Easily applied with rolls or brushes.

PROPERTIES

- Creates a strong, suitable primer under epoxy and polyurethane coatings.
- Protects the adherence of the coating to be applied on itself, due to its resistance to moisture from the negative.
- Penetrates well due to its low viscosity.
- Has very good mechanical strength.

MECHANICAL PROPERTIES

Mixture Ratio (A:B)	100:50 (by weight)
Density (20 °C de)	1,09 ± gr /cm ³
Viscosity (23 °C de)	350-600 m Pa.s
Working Time (20 °C de)	Approximately 25 minutes
Compressive Strength	50N/mm ² (7000)
Flexural Strength	20N/mm ² (7000)
Adhesion Strength	min.2N/mm ² (7000)
Shore D hardness	80
Ambient and Material Temperature	inm.8 °C-max. 30 °C
Curing time (at 23 °C)	1 week (7 days)
Walkable on after	8-12 hours
Chemical resistance	5 days

APPLICATION

Cured concrete surfaces must have a concrete quality of BS18 or minimum 350 dose and it must be minimum 3 weeks old. Foam layer on the surface must be removed with Blastrac or wiping machines, dust layer must be removed with industrial vacuums and the floor must be free of dirt and oils. Tensile strength of the floor concrete must be minimum 1.5N/mm² and humidity must be maximum +6 °C.

APPLICATION METHOD

First, Component A must be mixed well for 1-2 minutes with a low-speed mechanical mixer. Then Component B must be added and mixed well. The resulting homogeneous mixture will be applied on the floor with a roll brush or a level comb. If epoxy or polyurethane coating will be made on the moisture barrier, silica sand (0,8-1 kg/m²) with grain diameter of 0,1-0,3 mm. or 0,3-0,8 mm depending on the system, while the **ONKAPOX WET 365** is still wet.

CHEMICAL RESISTANCE

ONKAPOX WET 365 is resistant against dilute acids, lye, saline solutions, mineral oils and many other chemicals. You can ask our technical department for a chemical resistance chart if necessary.

PACKAGING

As a two-component kit: total 12 kg
Component A : 8.00 kg
Component B : 4.00 kg

CONSUMPTION

0,200-0,400 kg/m², depending on the quality of the concrete.

SHELF LIFE

Can be stored for 18 months in a dry and cool place, in its original unopened packaging.

SAFETY MEASURES

Components must not contact with the skin or the eyes or the foods, due to their irritant properties. Any areas of contact with the material must be washed with plenty of water and soap and a physician must be consulted in serious cases. Gloves must be worn during application. Do not approach the working site with fire.